CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-12-15-02** **Date: 18/12/2017**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Widening of Doddabommasandra Main road in Ward no.10

Agency : M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.

Customer's Reference : BBMP/BZ/EE(PR)/WO/01//2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-12-17

Sample ID No : 2017-12-15-02/03

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/12/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	11/12/2017	18/12/2017	150.47 X 150.33 X 149.58	22620	8.145	477.3	21.1	21.1
2	Cement Concrete	M20	11/12/2017	18/12/2017	151.21 X 150.66 X 149.87	22781	8.198	473.9	20.8	
3	Cement Concrete	M20	11/12/2017	18/12/2017	150.66 X 149.78 X 150.66	22566	8.169	482.9	21.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Vellankalla Zone
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-12-15-02** **Date: 08/01/2018**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Widening of Doddabommasandra Main road in Ward no.10

Agency : M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.

Customer's Reference : BBMP/BZ/EE(PR)/WO/01//2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-12-17

Sample ID No : 2017-12-15-02/04

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	11/12/2017	08/01/2018	150.47 X 150.33 X 149.58	22620	8.145	477.3	21.1	21.1
2	Cement Concrete	M20	11/12/2017	08/01/2018	151.21 X 150.66 X 149.87	22781	8.198	473.9	20.8	
3	Cement Concrete	M20	11/12/2017	08/01/2018	150.66 X 149.78 X 150.66	22566	8.169	482.9	21.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2017-12-15-02**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Widening of Doddabommasandra Main road in Ward no.10
Agency	:	M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.
Customer's Reference	:	BBMP/BZ/EE(PR)/WO/01//2015-16
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-12-17
Sample ID No	:	2017-12-15-02/05
Customer ID	:	Cement Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	19/12/2017

Date: 19/12/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	12/12/2017	19/12/2017	150.47 X 150.33 X 149.58	22620	8.145	477.3	21.1	21.1
2	Cement Concrete	M20	12/12/2017	19/12/2017	151.21 X 150.66 X 149.87	22781	8.198	473.9	20.8	
3	Cement Concrete	M20	12/12/2017	19/12/2017	150.66 X 149.78 X 150.66	22566	8.169	482.9	21.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Velahanka
Bang

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-12-15-02** **Date: 09/01/2018**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Widening of Doddabommasandra Main road in Ward no.10

Agency : M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.

Customer's Reference : BBMP/BZ/EE(PR)/WO/01//2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-12-17

Sample ID No : 2017-12-15-02/06

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	12/12/2017	09/01/2018	150.47 X 150.33 X 149.58	22620	8.145	477.3	21.1	
2	Cement Concrete	M20	12/12/2017	09/01/2018	151.21 X 150.66 X 149.87	22781	8.198	473.9	20.8	21.1
3	Cement Concrete	M20	12/12/2017	09/01/2018	150.66 X 149.78 X 150.66	22566	8.169	482.9	21.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Bangalore

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-12-15-02** **Date: 19/12/2017**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Widening of Doddabommasandra Main road in Ward no.10

Agency : M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.

Customer's Reference : BBMP/BZ/EE(PR)/WO/01//2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-12-17

Sample ID No : 2017-12-15-02/07

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/12/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	12/12/2017	19/12/2017	150.47 X 150.33 X 149.58	22620	8.145	477.3	21.1	21.1
2	Cement Concrete	M20	12/12/2017	19/12/2017	151.21 X 150.66 X 149.87	22781	8.198	473.9	20.8	
3	Cement Concrete	M20	12/12/2017	19/12/2017	150.66 X 149.78 X 150.66	22566	8.169	482.9	21.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Sundaresh A.E
20/12/2018
Asst. Executive Engineer
Project Division
Bangalore

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-12-15-02**

Date: 09/01/2018

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Widening of Doddabommasandra Main road in Ward no.10

Agency : M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.

Customer's Reference : BBMP/BZ/EE(PR)/WO/01//2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-12-17

Sample ID No : 2017-12-15-02/08

Customer ID : Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete	M20	12/12/2017	09/01/2018	150.47 X 150.33 X 149.58	22620	8.145	477.3	21.1	21.1
2	Cement Concrete	M20	12/12/2017	09/01/2018	151.21 X 150.66 X 149.87	22781	8.198	473.9	20.8	
3	Cement Concrete	M20	12/12/2017	09/01/2018	150.66 X 149.78 X 150.66	22566	8.169	482.9	21.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

30/1/2018

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-12-26-01** **Date: 30/12/2017**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Widening of Doddabommasandra Main road in Ward no.10

Agency : M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.

Customer's Reference : BBMP/BZ/EE(PR)/WO/01//2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-12-17

Sample ID No : 2017-01-26-01/01

Customer ID : M20 Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 30/12/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Cement Concrete	M20	23/12/2017	30/12/2017	149.65 X 151.22 X 149.78	22630	8.152	380.2	16.8	16.8
2	M20 Cement Concrete	M20	23/12/2017	30/12/2017	151.33 X 149.75 X 151.44	22662	8.197	387.5	17.1	
3	M20 Cement Concrete	M20	23/12/2017	30/12/2017	151.85 X 150.47 X 150.99	22849	8.161	377.0	16.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sri Sundaresh AE
received 30.12.17
Asst. Executive Engineer
Project Sub Division
Yelahanka
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-12-26-01** **Date: 20/01/2018**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Widening of Doddabommasandra Main road in Ward no.10

Agency : M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.

Customer's Reference : BBMP/BZ/EE(PR)/WO/01//2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-12-17

Sample ID No : 2017-01-26-01/02

Customer ID : M20 Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 20/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Cement Concrete	M20	23/12/2017	20/01/2018	151.42 X 150.35 X 150.28	22766	8.175	525.9	23.1	23.2
2	M20 Cement Concrete	M20	23/12/2017	20/01/2018	151.44 X 150.39 X 150.25	22775	8.198	539.8	23.7	
3	M20 Cement Concrete	M20	23/12/2017	20/01/2018	150.47 X 150.66 X 150.69	22670	8.135	516.9	22.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sw Sudhir AE
Accepted 30/12/2018
Asst. Engineer
Project Sub Division
Yelahanka
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-05-01** **Date: 10/01/2018**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Widening of Doddabommasandra Main road in Ward no.10

Agency : M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.

Customer's Reference : BBMP/BZ/EE(PR)/WO/01//2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-01-18

Sample ID No : 2018-01-05-01/01

Customer ID : M20 Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Cement Concrete	M20	03/01/2018	10/01/2018	150.31 X 150.64 X 150.77	22643	8.098	412.1	18.2	17.6
2	M20 Cement Concrete	M20	03/01/2018	10/01/2018	150.49 X 151.68 X 150.97	22826	8.158	390.3	17.1	
3	M20 Cement Concrete	M20	03/01/2018	10/01/2018	150.33 X 150.45 X 151.26	22617	8.174	398.1	17.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sri Sudhir Kr
Asst. Executive Engineer
Project
Volu
Ban
Surendra JE

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-01-05-01**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Widening of Doddabommasandra Main road in Ward no.10
Agency	:	M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.
Customer's Reference	:	BBMP/BZ/EE(PR)/WO/01//2015-16
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-01-18
Sample ID No	:	2018-01-05-01/02
Customer ID	:	M20 Cement Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	31/01/2018

Date: 31/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Cement Concrete	M20	03/01/2018	31/01/2018	150.38 X 150.78 X 150.66	22674	8.147	530.6	23.4	23.3
2	M20 Cement Concrete	M20	03/01/2018	31/01/2018	150.47 X 150.98 X 150.38	22718	8.198	515.7	22.7	
3	M20 Cement Concrete	M20	03/01/2018	31/01/2018	149.87 X 149.58 X 151.45	22418	8.152	533.5	23.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sri. Sudhir DE
Received on 30/1/18
Project Engineer
JE

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-01-20-01** **Date: 23/01/2018**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Widening of Doddabommasandra Main road in Ward no.10

Agency : M/s Prashanth Road Infra Projects and Develpers Pvt.Ltd.

Customer's Reference : BBMP/BZ/EE(PR)/WO/01//2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-18

Sample ID No : 2018-01-20-01/01

Customer ID : M20 Cement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 23/01/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Cement Concrete	M20	16/01/2018	23/01/2018	149.28 X 150.44 X 150.32	22458	8.198	386.3	17.2	17.2
2	M20 Cement Concrete	M20	16/01/2018	23/01/2018	150.44 X 150.26 X 149.85	22605	8.147	395.6	17.5	
3	M20 Cement Concrete	M20	16/01/2018	23/01/2018	151.33 X 150.33 X 151.47	22749	8.165	384.5	16.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sig. Sudhir AE
30/1/2018
JE

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****